

Classifications

AWS A5.5 / SFA-5.5	AWS A5.5M	EN ISO 2560-A	EN ISO 2560-B
E7010-A1	E4910-A1	E 42 3 Mo C 2 5	E4910-M3 A

Characteristics and typical fields of application

Mo-alloyed cellulose coated electrode for vertical-down welding of high strength large diameter pipelines. Highly economical compared with conventional vertical-up welding. Especially recommended for hot passes, filler and cover layers.

Excellent weld-metal toughness, easy welding, with an intensive arc and a deep penetration in order to ensure sound joint welds with good X-ray quality.

BÖHLER FOX CEL Mo can be used in sour gas applications (HIC-Test acc. NACE TM-02-84). Test values for SSC-test are available too.

Base materials

S235JR, S275JR, S235J2G3, S275J2G3, S355J2G3, P235GH, P265GH, L210 - L415NB, L290MB-L415MB, P355T1, P235T2 - P355T2, P235G1TH, P255G1TH

Root pass up to L555MB

API Spec. 5 L: Grade A, B, X 42, X 46, X 52, X 56, X 60

Root pass up to X 80

Typical analysis

	C	Si	Mn	Mo
wt.-%	0.1	0.14	0.4	0.5

Mechanical properties of all-weld metal - typical values (min. values)

Condition	Yield strength R _e	Tensile strength R _m	Elongation A (L ₀ =5d ₀)	Impact energy ISO-V KV J				
	ksi	ksi	%	68°F	32°F	-4°F	-22°F	-40°F
u	70 (≥ 61)	80 (500-640)	23 (≥ 20)	74 ftlb	70 ftlb	63 ftlb	37 (≥ 35) ftlb	31 ftlb

u untreated, as welded

Operating data

	Polarity	DC +/–, negative polarity for root pass possible	Dimension inch	Current A
	Electrode identification	FOX CEL Mo 7010-A1 E 42 3 Mo C	1/8" × 14"	80 – 130
			5/32" × 14"	120 – 180
	Redrying	not allowed	~3/16" × 14"	160 – 210

Approvals

TÜV (01325.), ABS, CE